

PlastKYD L661 N60

Date of edition: 05.05.2009
Date of updating: 05.10.2016

DESCRIPTION

Long oil alkyd resin modified with linseed oil containing cca. 65% oil, delivered as 60% solution in aromatic-free white spirit.

APPLICATIONS

PlastKYD L661 N60 is suitable for general applications. It can be used for production of paints intended for painting of wooden and metal elements inside and outside of buildings.

PROPERTIES

Viscosity , Brookfield, 20 rpm, spindle 3, 20°C approx.	300	mPa·s	PN-EN ISO 2555
Flow time , Ford Cub ϕ 4mm, 20 °C, 60% in aromatic-free WS D40	250-350	s	PN-C-81701 method A
Density , 20°C	0,90±0,02	g/cm ³	PN-82/C81551 method B
Acid value , max.	10	mg KOH/g	PN-85/C-04066
Colour , max.	20	mg I ₂ /100 cm ³	PN-84/C-04534/02
Non volatile content	60±2	%	PN-EN ISO 3251

GUARANTEE PERIOD

12 months from the production date.

TRANSPORT & STORAGE

Transport and store in tightly closed containers at temperatures below 30°C.

PACKAGING

Pallet container 1000 l, tank truck or other packaging agreed with the customer.

H&S INFORMATION

Raw materials used for manufacture of the resin are flammable and harmful if swallowed, inhaled or in the case of contact with the skin.

Further information about hazardous influences and protection are detailed in the material safety data sheet.

The data are based on our current knowledge and are intended to provide general notes on our products, their technical data and applications. They do not relieve processors from carrying out their own investigations and tests. They also cannot be regarded as a guarantee in the legal sense.